

EasyWeed[®], EasyWeed[®] Extra, EasyWeed[®] Electric, EasyWeed[®] Glow

For Use On: 100% cotton | Poly/cotton blends | 100% polyester | Leather



Application Instructions (Home Iron):

- Set iron dial between Cotton and Linen
- Cover design with Kraft Paper or non-stick cover sheet
- Place on flat, hard surface (ironing board not recommended)
- Press iron with medium/firm pressure for 10-15 seconds
- * If areas lift after application, cover and press for 5-10 seconds.
- Peel carrier hot or cold

Application Instructions (Heat Press):

- Cut in reverse and weed excess material
- Preheat garment for 2-3 seconds
- Apply design at 305°F / 150°C (EasyPress[®] users add approx. 30°)
- Use medium pressure for 10-15 seconds
- Peel carrier hot or cold

Laundering:

- Wait 24 hours before first wash
- Machine wash warm or cold with mild detergent
- Do not bleach or dry clean
- Dry on normal dryer setting

EasyWeed[®] Stretch (matte)

For Use On: 100% cotton | Poly/cotton blends | 100% polyester | Leather



Application Instructions (Home Iron):

- Set iron dial between Cotton and Linen
- Cover design with Kraft Paper or non-stick cover sheet
- Place on flat, hard surface (ironing board not recommended)
- Press iron with firm pressure for 20 seconds
- * If areas lift after application, cover and press for 5-10 seconds.
- Peel carrier hot or cold

Application Instructions (Heat Press):

- Cut in reverse and weed excess material
- Preheat garment for 2-3 seconds
- Apply design at 320°F / 160°C (EasyPress[®] users add approx. 30°)
- Use firm pressure for 20 seconds
- Peel carrier hot or cold

Laundering:

- Wait 24 hours before first wash
- Machine wash cold with mild detergent
- Do not bleach or dry clean
- Dry on normal setting

EasyWeed[®] Sub Block

For Use On: 100% cotton | Poly/cotton blends | 100% polyester | Leather



Application Instructions (Home Iron):

- Set iron dial between Cotton and Linen
- Cover design with Kraft Paper or non-stick cover sheet
- Place on flat, hard surface (ironing board not recommended)
- Press iron with medium/firm pressure for 10-15 seconds
- * If areas lift after application, cover and press for 5-10 seconds.
- Peel carrier hot or cold

Application Instructions (Heat Press):

- Cut in reverse and weed excess material
- Preheat garment for 2-3 seconds
- Apply design at 265°F / 130°C (EasyPress[®] users add approx. 30°)
- Use medium pressure for 10-15 seconds
- Peel carrier hot or cold

Laundering:

- Wait 24 hours before first wash
- Machine wash cold with mild detergent
- Do not bleach or dry clean
- Hang item to dry

EasyWeed[®] Adhesive

For Use On: 100% cotton | Poly/cotton blends | 100% polyester



Application Instructions (Home Iron):

- Set iron dial between Cotton and Linen
- Cover design with Kraft Paper or non-stick cover sheet
- Place on flat, hard surface (ironing board not recommended)
- Press iron with medium/firm pressure for 10-15 seconds
- * If areas lift after application, cover and press for 5-10 seconds.
- Peel carrier hot

Application Instructions (Heat Press):

- Cut in reverse and weed excess material
- Preheat garment for 2-3 seconds
- Apply design at 275°F / 135°C (EasyPress[®] users add approx. 30°)
- Use medium pressure for 5-10 seconds
- Peel carrier hot then apply top layer

Laundering:

- Wait 24 hours before first wash
- Machine wash warm or cold with mild detergent
- Do not bleach or dry clean
- Dry on normal dryer setting

EasyPatterns[®]

For Use On: 100% cotton | Poly/cotton blends | 100% polyester | Leather



Application Instructions (Home Iron):

- Set iron dial between Cotton and Linen
- Cover design with Kraft Paper or non-stick cover sheet
- Place on flat, hard surface (ironing board not recommended)
- Press iron with medium/firm pressure for 10-15 seconds
- * If areas lift after application, cover and press for 10 seconds.
- Peel carrier hot or cold

Application Instructions (Heat Press):

- Cut design (do not mirror), weed then mask
- Preheat garment for 2-3 seconds
- Apply design at 305°F / 150°C (EasyPress[®] users add approx. 30°)
- Use medium pressure for 10-15 seconds
- Peel carrier hot or cold
- Cover and reheat for 2-3 seconds

Laundering:

- Wait 24 hours before first wash
- Machine wash cold with mild detergent
- Do not bleach or dry clean
- Dry on normal dryer setting

EasyReflective[®]

For Use On: 100% cotton | Poly/cotton blends | 100% polyester | Leather | Lycra[®]/Spandex



Application Instructions (Home Iron):

- Set iron dial between Cotton and Linen
- Cover design with Kraft Paper or non-stick cover sheet
- Place on flat, hard surface (ironing board not recommended)
- Press iron with medium/firm pressure for 10-15 seconds
- * If areas lift after application, cover and press for 10 seconds.
- Peel carrier warm

Application Instructions (Heat Press):

- Cut in reverse and weed excess material
- Preheat garment for 2-3 seconds
- Apply design at 305°F / 150°C (EasyPress[®] users add approx. 30°)
- Use medium pressure for 15 seconds
- Peel carrier warm (wait at least 15 seconds)

Laundering:

- Wait 24 hours before first wash
- Machine wash warm or cold with mild detergent
- Do not bleach or dry clean
- Dry on normal dryer setting

Blackboard[®]

For Use On: 100% cotton | Poly/cotton blends | 100% polyester



Application Instructions (Home Iron):

- Set iron dial between Cotton and Linen
- Cover design with Kraft Paper or non-stick cover sheet
- Place on flat, hard surface (ironing board not recommended)
- Press iron with medium/firm pressure for 10-15 seconds
- * If areas lift after application, cover and press for 10 seconds.
- Peel carrier warm

Application Instructions (Heat Press):

- Cut in reverse and weed excess material
- Preheat garment for 2-3 seconds
- Apply design at 275°F / 135°C (EasyPress[®] users add approx. 30°)
- Use medium pressure for 15 seconds
- Peel carrier warm

Laundering:

- Wait 24 hours before first wash
- Machine wash cold with mild detergent
- Do not bleach or dry clean
- Dry on normal dryer setting

Glitter

For Use On: 100% cotton | Poly/cotton blends | 100% polyester | Leather



Application Instructions (Home Iron):

- Set iron dial between Cotton and Linen
- Cover design with Kraft Paper or non-stick cover sheet
- Place on flat, hard surface (ironing board not recommended)
- Press iron with medium/firm pressure for 10-15 seconds
- If areas lift after application, cover and press for 10 seconds.
- Peel carrier warm

Application Instructions (Heat Press):

- Cut in reverse and weed excess material
- Preheat garment for 2-3 seconds
- Apply design at 320°F / 160°C (EasyPress® users add approx. 30°)
- Use medium pressure for 15-20 seconds
- Peel carrier warm

Laundering:

- Wait 24 hours before first wash
- Machine wash warm or cold with mild detergent
- Do not bleach or dry clean
- Dry on normal dryer setting

Twinkle™

For Use On: 100% cotton | Poly/cotton blends | 100% polyester



Application Instructions (Home Iron):

- Set iron dial between Cotton and Linen
- Cover design with Kraft Paper or non-stick cover sheet
- Place on flat, hard surface (ironing board not recommended)
- Press iron with medium/firm pressure for 15 seconds
- If areas lift after application, cover and press for 10 seconds.
- Peel carrier warm

Application Instructions (Heat Press):

- Cut in reverse and weed excess material
- Preheat garment for 2-3 seconds
- Apply design at 305°F / 150°C (EasyPress® users add approx. 30°)
- Use medium/firm pressure for 15 seconds
- Peel carrier warm

Laundering:

- Wait 24 hours before first wash
- Machine wash cold with mild detergent
- Do not bleach or dry clean
- Dry on low setting

Sparkle™

For Use On: 100% cotton | Poly/cotton blends | 100% polyester | Leather



Application Instructions (Home Iron):

- Set iron dial between Cotton and Linen
- Cover design with Kraft Paper or non-stick cover sheet
- Place on flat, hard surface (ironing board not recommended)
- Press iron with medium pressure for 10-15 seconds
- If areas lift after application, cover and press for 5-10 seconds.
- Peel carrier hot or cold

Application Instructions (Heat Press):

- Cut in reverse and weed excess material
- Preheat garment for 2-3 seconds
- Apply design at 305°F / 150°C (EasyPress® users add approx. 30°)
- Use medium/firm pressure for 10-15 seconds
- Peel carrier hot or cold

Laundering:

- Wait 24 hours before first wash
- Machine wash cold with mild detergent
- Do not bleach or dry clean
- Dry on low setting

Holographic

For Use On: 100% cotton | Poly/cotton blends | 100% polyester | Leather



Application Instructions (Home Iron):

- Set iron dial between Cotton and Linen
- Cover design with Kraft Paper or non-stick cover sheet
- Place on flat, hard surface (ironing board not recommended)
- Press iron with medium/firm pressure for 10-15 seconds
- If areas lift after application, cover and press for 5-10 seconds.
- Peel carrier cold

Application Instructions (Heat Press):

- Cut in reverse and weed excess material
- Preheat garment for 2-3 seconds
- Apply design at 320°F / 160°C (EasyPress® users add approx. 30°)
- Use medium pressure for 15-20 seconds
- Peel carrier cold

Laundering:

- Wait 24 hours before first wash
- Machine wash warm or cold with mild detergent
- Do not bleach or dry clean
- Dry on normal dryer setting

Metal

For Use On: 100% cotton | Poly/cotton blends | 100% polyester



Application Instructions (Home Iron):

- Set iron dial between Cotton and Linen
- Cover design with Kraft Paper or non-stick cover sheet
- Place on flat, hard surface (ironing board not recommended)
- Press iron with medium/firm pressure for 10-15 seconds
- If areas lift after application, cover and press for 5-10 seconds.
- Peel carrier cold

Application Instructions (Heat Press):

- Cut in reverse and weed excess material
- Preheat garment for 2-3 seconds
- Apply design at 305°F / 150°C (EasyPress® users add approx. 30°)
- Use medium pressure for 10-15 seconds
- Peel carrier cold

Laundering:

- Wait 24 hours before first wash
- Machine wash cold with mild detergent
- Do not bleach or dry clean
- Dry on low dryer setting

StripFlock® Pro

For Use On: 100% cotton | Poly/cotton blends | 100% polyester | Leather



Application Instructions (Home Iron):

- Set iron dial between Cotton and Linen
- Cover design with Kraft Paper or non-stick cover sheet
- Place on flat, hard surface (ironing board not recommended)
- Press iron with medium/firm pressure for 10-15 seconds
- If areas lift after application, cover and press for 10 seconds.
- Peel carrier warm

Application Instructions (Heat Press):

- Cut in reverse and weed excess material
- Preheat garment for 2-3 seconds
- Apply design at 311°F / 155°C (EasyPress® users add approx. 30°)
- Use medium pressure for 10-15 seconds
- Peel carrier warm

Laundering:

- Wait 24 hours before first wash
- Machine wash warm or cold with mild detergent
- Do not bleach or dry clean
- Dry on normal dryer setting

Brick® 600

For Use On: 100% cotton | Poly/cotton blends | 100% polyester



Application Instructions (Home Iron):

- Set iron dial between Cotton and Linen
- Cover design with Kraft Paper or non-stick cover sheet
- Place on flat, hard surface (ironing board not recommended)
- Press iron with medium/firm pressure for 10-15 seconds
- If areas lift after application, cover and press for 10 seconds.
- Peel carrier cold

Application Instructions (Heat Press):

- Cut in reverse and weed excess material
- Preheat garment for 2-3 seconds
- Apply design at 311°F / 155°C (EasyPress® users add approx. 30°)
- Use medium/firm pressure for 20 seconds
- Peel carrier cold

Laundering:

- Wait 24 hours before first wash
- Machine wash warm or cold with mild detergent
- Do not bleach or dry clean
- Dry on low dryer setting